

HARDFACING MIG GLX 600 GASLESS HARDFACING

FEATURES

- New generation self shielding (gasless) flux cored wire.
- High carbon austenitic steel deposit. Ideal for high surface abrasion and low impact.
- Very low fume and spatter levels.
- 0.9mm wire can be used on a single phase 240 volt, 90 - 250 amp MIG welders.
- All positional for single and multi pass applications.

APPROVALS & CLASSIFICATION

- AS/NZS 2576
- 1865 - B7

APPLICATIONS

Hard facing of agricultural, mining and material handling equipment including;

- tyne points
- conveyor screws
- buckets
- scraper blades
- cone harvester cutters
- dredge pumps
- sizing screens
- impellers



TECHNICAL DATA

Typical Weld Deposit Hardness

| | |
|----------------------------------|-----------|
| Single layer on mild steel - HRC | 58 - 62 |
| Multi layer on mild steel - HRC | 62 - 65 |
| Single layer on mild steel - HV | 680 - 780 |
| Multi layer on mild steel - HV | 780 - 860 |

Typical All Weld Metal Analysis

| Carbon | Manganese | Silicon |
|---------|-----------|---------|
| 1.62% | 1.32% | 0.61% |
| Sulphur | Chromium | |
| 0.0021% | 4.80% | |

Operating Data

| Wire Dia. | Current Range | Voltage | Polarity |
|-----------|---------------|---------|-------------|
| 0.9mm | 90 - 180 | 16 - 20 | DC Negative |
| 1.2mm | 120 - 220 | 18 - 24 | DC Negative |

ORDERING INFO

| Part Number | Size | Packet |
|-------------|-------|--------|
| 200393 | 0.9mm | 1kg |
| 200394 | 0.9mm | 3kg |
| 200395 | 0.9mm | 5kg |
| 200396 | 0.9mm | 15kg |
| 200397 | 1.2mm | 15kg |